



Technische specificatie nr. TS MG32-5	 23	 K-0211070	 1916-20-BBK
Uitgiftedatum: 15-9-2026	0063-CPR-300081 DoP nr. MG32-260915		

Menggranulaat 0/31,5 mm.

EN 13242:2002+A1:2007

Toeslagmateriaal voor ongebonden en hydraulisch gebonden materialen voor civieltechnische- en wegenbouw

Zeef (mm)	63	45	31,5	22,4	16	11,2	8	5,6	4	2	1	0,500	0,063
Gem. doorval (%)	100	100	92	80	69	57	48	40	35	28	24	19	3,3
Min. Norm	100	-	75	-	50	-	30	-	20	13	8	5	0
Max norm	-	-	100	-	90	-	75	-	60	45	35	30	7

Prestaties	
Korrelgrootte	0/31,5
Gradering	G _A 75
Korrelvorm-vlakheidsindex	FI ₂₀
Gehalte fijne bestanddelen	f ₇
Weerstand tegen verbrijzeling	LA ₆₀
Korrel dichtheid	≥ 2,00 Mg/m ³
Waterabsorptie	≤ 10,5 %
Classificatie van grove recyclinggranulaten	Rc45declared , Rcug50 , Rb50-, Ra5-, Rg _{NR} , X1- , FL ₁₀ -
Gehalte asbest	< 100 mg/kg d.s.
Samenstelling organische stoffen	Voldoet aan Bbk
Uitloging o.a. zware metalen	Voldoet aan Bbk

Naam:	M. de Koning	Datum:	15-09-2026
Functie:	Kwaliteitscoördinator	Handtekening:	